

TECHNICAL DATA

# “PIETRE NATURALI” Series- White Body Wall Tile

## 1. Technical Features

UNI EN 14411 - Annex L –Dry-pressed ceramic tiles - GROUP BIII GL

	Technical features	Norms	Required standards	Average
<b>REGULARITY AND QUALITY SURFACE CHARACTERISTICS</b>	LENGTH AND WIDTH (The deviation, in percent, of the average size for each tile (2 or 4 sides) from the work size (W))	UNI EN ISO 10545-2	± 0,6 %	IN ACCORDANCE
	THICKNESS		± 5 %	IN ACCORDANCE
	STRAIGHTNESS OF SIDES		± 0,3 %	IN ACCORDANCE
	RECTANGULARITY		± 0,5 %	IN ACCORDANCE
	SURFACE FLATNESS		+ 0,5 % , -0,3% (Curvatura centro e spigolo) ± 0,5 % (svergolamento)	IN ACCORDANCE
	SURFACE QUALITY		A minimum of 95% of tiles shall be free from visible defects that would impair the appearance of a major area of tiles	IN ACCORDANCE
<b>PHISICAL CHARACTERISTICS</b>	WATER ABSORPTION	UNI EN ISO 10545-3	10 % < Eb (<20 %)	IN ACCORDANCE
	BREAKING STRENGTH (S) – MODULUS OF RUPTURE (R)	UNI EN ISO 10545-4	S > 600 N R > 15 N/mm <sup>2</sup>	IN ACCORDANCE
	CRAZING RESISTANCE	UNI EN ISO 10545-11	REQUIRED	IN ACCORDANCE
<b>CHEMICAL CHARACTERISTICS</b>	RESISTANCE TO HOUSEHOLD CHEMICALS AND SWIMMING POOL SALTS	UNI EN ISO 10545-13	Class GB min.	RESISTANT
	RESISTANCE TO LOW CONCENTRATIONS OF ACIDS AND ALKALIS		Manufacturer to state classification	RESISTANT
	RESISTANCE TO STAINING	UNI EN ISO 10545-14	Minimum Class 3	IN ACCORDANCE

## 2. Sizes, Finishings:

2.1 Sizes: 32.5x65

2.2 Colours: 3 (Moka Cream, Mokacream Sabbia, Mokacream Caffè)

2.2 Finishings: Rectified

## 3. Process features

The PIETRE NATURALI series is realized in porcelain stoneware by dry pressing of a mix of spray-dried bodies obtained from precious natural raw materials. The obtained substrate is later silk-screen printed (decorated) and fired at over 1100°C, temperature needed to reach the sintering necessary to make the product frost-proof, non-

absorbing and resistant to chemical attacks.

#### 4. In accordance with standards



EN 14411



PIETRE NATURALI is a material that ensures compliance, as far as the first choice is concerned, with the requirements specified in the international standards UNI EN 14411 appendix G and ISO 13006, for the surface chemical and physical features; the compliance is extended to all commercial choices for the safety features connected with the CE marking. PIETRE NATURALI is also CCC certified.

The Quality management system - implemented by the company and certified according to the standard UNI EN ISO 9001:2008 - ensures a steady compliance.



#### 5. Environmental Certification



##### 5.1 ANAB-ICEA

**Naxos**, for PIETRE NATURALI, has successfully gained the ANAB-ICEA product labeling which, according to the requirements of the EN ISO 14024 norm, ensures that the products bearing the ANAB mark:

- are obtained from raw materials mined with a reduced environmental impact
- do not contain substances harmful for man and the environment
- are obtained from a productive process which is strictly checked and with a reduced environmental impact
- do not release polluting substances in the surrounding environment.

The ANAB certification can aid reaching the requirements needed to obtain the benefit granted by the new Italian HOME PLAN (at least in regions relating the cubage benefits with the use of bio-building materials and techniques).

##### 5.2 LEED Rating System



PIETRE NATURALI guarantees the following LEED credits:

**Credit SS 7.1/7.2 - Heat Island Effect:** PIETRE NATURALI does not increase the temperature of city areas compared to country areas (No heat island effect), as the solar reflectance index SRI is  $\geq 29$ . PIETRE NATURALI is thus particularly suitable for outdoor roofed and non-roofed installations.(

**Credit EA 1 - Optimize energy performance:** heat conductivity  $\lambda$  of PIETRE NATURALI ranges between 1 and 1.3 Watt/(m·K). Therefore PIETRE NATURALI is provided of very good insulating performance.(

**Credit EQ 4.2 - VOC content:** PIETRE NATURALI does not emit VOC (Volatile Organic Compounds), as certified by qualified external laboratories.

**Credit MR 1.2 - Building re-use:** PIETRE NATURALI can contribute to this credit by coating existing floors and walls, renovating surfaces and structures avoiding their demolition and rebuilding.

**Credit MR 2.1-2.2 - Management of building wastes:** PIETRE NATURALI can contribute to this credit, as all ceramic tiles can be totally considered as recovered materials to be used as aggregates for different filling operations (substrates, embankments, etc.).

**Credit MR 5.1-5.2 – Regional materials:** 65% of the materials used to produce PIETRE NATURALI comes from quarries located within 500 miles from its production headquarters.

**Credits ID 1.1-1.4 - Innovation in Design :**

- PIETRE NATURALI is ANAB/ICEA certified and this is an innovative performance as for the environmental benefits offered by the product.

## TECHNICAL DATA

# “PIETRE NATURALI” Series – Porcelain Floors

## 1. Technical Features

UNI EN 14411 - Annex G –Dry-pressed ceramic tiles with low water absorption - GROUP B1aGL

	Technical features	Norms	Required standards	Average
REGULARITY AND QUALITY SURFACE CHARACTERISTICS	LENGTH AND WIDTH (The deviation, in percent, of the average size for each tile (2 or 4 sides) from the work size (W))	UNI EN ISO 10545-2	± 0,6 %	IN ACCORDANCE
	THICKNESS		± 5 %	IN ACCORDANCE
	STRAIGHTNESS OF SIDES		± 0,5 %	IN ACCORDANCE
	RECTANGULARITY		± 0,6 %	IN ACCORDANCE
	SURFACE FLATNESS		± 0,5 %	IN ACCORDANCE
	SURFACE QUALITY		A minimum of 95% of tiles shall be free from visible defects that would impair the appearance of a major area of tiles	IN ACCORDANCE
PHYSICAL CHARACTERISTICS	WATER ABSORPTION	UNI EN ISO 10545-3	Eb ≤ 0,5 %	IN ACCORDANCE
	BREAKING STRENGTH (S) – MODULUS OF RUPTURE (R)	UNI EN ISO 10545-4	S > 1300 N R > 35 N/mm <sup>2</sup>	IN ACCORDANCE
	CRAZING RESISTANCE	UNI EN ISO 10545-11	REQUIRED	IN ACCORDANCE
	RESISTANCE TO FROST	UNI EN ISO 10545-12	REQUIRED	IN ACCORDANCE
CHEMICAL CHARACTERISTICS	RESISTANCE TO HOUSEHOLD CHEMICALS AND SWIMMING POOL SALTS	UNI EN ISO 10545-13	Class GB min.	RESISTANT
	RESISTANCE TO LOW CONCENTRATIONS OF ACIDS AND ALKALIS		Manufacturer to state classification	RESISTANT
	RESISTANCE TO STAINING	UNI EN ISO 10545-14	Minimum Class 3	IN ACCORDANCE

## 2. Sizes, Finishings:

NAXOS • Strada Statale, 569, n°169 • 41050 Solignano (MO) Italia • Tel. +39 059 • 74.88.11 • Fax +39 059 • 79.73.76  
Internet: <http://www.naxos-ceramica.it> • e-mail: [info@naxos-ceramica.it](mailto:info@naxos-ceramica.it)

FINCIBEC S.p.A.

Via Valle D'Aosta, 47 • 41049 Sassuolo • Modena • Italia • Tel. +39 0536 861.300 • Fax Uff. Amministrazione +39 0536 861.351 • C.P. n. 175.176  
Cap. Soc. € 5.000.000,00 int. vers. • Reg. Imp. n. 00668210362 • MO • REA MO 88786 • M. MO 030229 • Cod. Fiscale 00668210362 • Part. IVA 01024300368  
CODICE IDENTIFICATIVO IT 01024300368 • Internet: <http://www.fincibec.it> • e-mail: [info@fincibec.it](mailto:info@fincibec.it)

GRUPPO FIRE - Fire S.R.L. Sede in Bologna Piazza Calderini N.5

**2.1 Sizes:** 32.5x32.5

**2.2 Colours:** 1 (Mokacream Caffè)

**2.2 Finishings:** Rectified

### **3. Process features**

The PIETRE NATURALI series is realized in porcelain stoneware by dry pressing of a mix of spray-dried bodies obtained from precious natural raw materials. The obtained substrate is later silk-screen printed (decorated) and fired at over 1200°C, temperature needed to reach the sintering necessary to make the product frost-proof, non-absorbing and resistant to chemical attacks.

### **4. In accordance with standards**



PIETRE NATURALI is a material that ensures compliance, as far as the first choice is concerned, with the requirements specified in the international standards UNI EN 14411 appendix G and ISO 13006, for the surface chemical and physical features; the compliance is extended to all commercial choices for the safety features connected with the CE marking. PIETRE NATURALI is also CCC certified.

The Quality management system - implemented by the company and certified according to the standard UNI EN ISO 9001:2008 - ensures a steady compliance.



### **5. Environmental Certification**



#### **5.2 ANAB-ICEA**

**Naxos**, for PIETRE NATURALI, has successfully gained the ANAB-ICEA product labeling which, according to the requirements of the EN ISO 14024 norm, ensures that the products bearing the ANAB mark:

- are obtained from raw materials mined with a reduced environmental impact
- do not contain substances harmful for man and the environment
- are obtained from a productive process which is strictly checked and with a reduced environmental impact
- do not release polluting substances in the surrounding environment.

The ANAB certification can aid reaching the requirements needed to obtain the benefit granted by the new Italian HOME PLAN (at least in regions relating the cubage benefits with the use of bio-building materials and techniques).

## 5.2 LEED Rating System

PIETRE NATURALI guarantees the following LEED credits:



**Credit SS 7.1/7.2 - Heat Island Effect:** PIETRE NATURALI does not increase the temperature of city areas compared to country areas (No heat island effect), as the solar reflectance index SRI is  $\geq 29$ . PIETRE NATURALI is thus particularly suitable for outdoor roofed and non-roofed installations.

**Credit EA 1 - Optimize energy performance:** heat conductivity  $\lambda$  of PIETRE NATURALI ranges between 1 and 1.3 Watt/(m·K). Therefore PIETRE NATURALI is provided of very good insulating performance.

**Credit EQ 4.2 - VOC content:** PIETRE NATURALI does not emit VOC (Volatile Organic Compounds), as certified by qualified external laboratories.

**Credit MR 1.2 - Building re-use:** PIETRE NATURALI can contribute to this credit by coating existing floors and walls, renovating surfaces and structures avoiding their demolition and rebuilding.

**Credit MR 2.1-2.2 - Management of building wastes:** PIETRE NATURALI can contribute to this credit, as all ceramic tiles can be totally considered as recovered materials to be used as aggregates for different filling operations (substrates, embankments, etc.).

**Credit MR 5.1-5.2 – Regional materials:** 65% of the materials used to produce PIETRE NATURALI comes from quarries located within 500 miles from its production headquarters.

**Credits ID 1.1-1.4 - Innovation in Design :**

- PIETRE NATURALI is ANAB/ICEA certified and this is an innovative performance as for the environmental benefits offered by the product.